


deceptively light

lift your margins with MULTIBOARD®



The most cost-effective choice in its class, providing high strength, high stiffness and high stackability - all at a lower grammage. 100% recycled, Multiboard Offset is made from 100% recovered cellulose fibres, giving it stiff advantage over its competitors.

For more information or to request samples please contact us:
t: +44 (0) 116 232 4102 www.warrenboard.co.uk



definitely strong



Board Comparison Chart

Current Grade	Cal/Gsm	Stiffness Taber 15°mNm		Multiboard Offset option	Stiffness Taber 15°mNm		Yield saving on Multiboard
		MD	CD		MD	CD	
Hermicoat Grey	480/350	21.0	8.8	445/325	21.3	8.2	7.7%
MCM	540/380	25.2	10.1	480/350	26.6	10.1	8.6%
Uniboard S	410/320	15.3	6.4	405/300	16.4	6.5	6.7%

All information from brand owner's own website/supplied by mill agent.

Product Specification

Caliper	Gsm	Std	Mill Stiffness 15°mNm	
			MD	CD
375	280	Y	13.30	5.30
405	300	Y	16.40	6.50
445	325	Y	21.30	8.20
480	350	Y	26.60	10.10
520	375	Y	32.40	12.30
555	400	Y	38.20	14.50
595	425	Y	45.20	16.90
630	450	Y	52.40	19.30
+/-5%	+/-3%		-15%	-15%

Multiboard comprises of five different basic grades:

- Multiboard Offset
- Multiboard Kraft
- Multiboard EcoFrost
- Multiboard EcoKraft
- Multiboard Barrier

All Multiboard grades are approved for direct contact with dry foods.

Multiboard Barrier is also approved for direct contact with fatty and moist foods.



For more information or to request samples please contact us:
t: +44 (0) 116 232 4102 www.warrenboard.co.uk

Printed on Multiboard Offset 375mic/280gsm.