

Dualwhite Skin

Technical Specification

Description: Dualwhite Skinboard (UT2)
Mill: Stadacona Inc - Canada

Board Type: Skin
Backing: White
Coating: Uncoated

Recycled Content: 100%

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
500	370	Y	0.00	0.00
600	435	Y	0.00	0.00
700	500	Y	0.00	0.00
800	570	Y	0.00	0.00
850	600	Y	0.00	0.00
900	640	Y	0.00	0.00
1025	720	Y	0.00	0.00
+/- 25			+/- 20%	+/- 20%

TEST DATA

Property	Test	Value	UOM	Tolerance
Brightness	ISO	Ave:80	%	Min 77%
Plybond		Ave:60	psi	Min 40
Porosity	Gurley	Ave:80	S/100cc	Max 125
Moisture		Ave:5.5	%	Min4%/Max7%

TEST & TECH. NOTES

MAKING NOTES

Minimum making 10 tonnes per caliper/gsm
 Min 3000 kgs per spec.