

Hansol

Technical Specification

Description: F/C WLC grey back (GD2)
Mill: Hansol - Mill

Board Type: Chip
Backing: Grey
Coating: Full

Coating Weight: 23-30gsm
Recycled Content: 95%

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
225	180	Y	2.90	1.30
250	200	Y	4.60	1.90
275	220	Y	5.80	2.40
285	230	Y	6.40	2.60
295	240	Y	7.10	2.70
315	250	Y	8.10	3.20
330	260	Y	8.60	3.50
355	280	Y	11.80	4.80
385	300	Y	13.40	5.10
425	330	N	14.70	8.00
455	350	Y	20.10	7.60
480	370	N	0.00	0.00
520	400	Y	28.60	11.10
590	450	Y	39.80	15.50
660	500	N	51.90	20.10
+/-20-	+/- 5%		-15%	-15%

TEST DATA

Property	Test	Value	UOM	Tolerance
Smoothness	Bekk	Min 60	secs	
Brightness	Elrepho	Min 76	%	+/-1
Gloss		Min 45	%	
Moisture		7	%	+/- 1.5

TEST & TECH. NOTES

MAKING NOTES

Minimum sheet size 450 x 450 mm
Maximum sheet size 1400 x 1400 mm
Above 280 gsm - 30 gsm coating weight
Below 280 gsm - 23 gsm coating weight

QUANTITY TOLERANCES

ORDERING INFORMATION

5000-10000 kgs: +/- 10%
10001-20000 kgs: +/- 7.5%
20001-50000 kgs: +/- 4%
50001 kgs+: +/-2.5%
Double tolerance if min/max quantity