

Litebk Skin/Crm

Technical Specification

Description: Liteback Skin/Cream (UT2)
Mill: Stadacona Inc - Canada

Board Type: Skin
Backing: Cream
Coating: Uncoated

Recycled Content: 100%

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
500	360	Y	0.00	0.00
600	425	Y	0.00	0.00
700	490	Y	0.00	0.00
850	585	Y	0.00	0.00
+/- 25			+/-20%	+/-20%

TEST DATA

Property	Test	Value	UOM	Tolerance
Brightness	ISO	Average 80	%	Min 77
Plybond	Psi	Average 55		Min 40
Porosity	Gurley	Average 100	s/100cc	Max 165
Moisture		Average 5.5	%	Min4/Max7

TEST & TECH. NOTES

MAKING NOTES

Minimum making 10 tonnes per caliper/gsm
 Min 3000 kgs per spec.