

Multiboard EcoKraft

Technical Specification

Description: F/C H/S WLC kraft back (GK4)
Mill: Fiskeby Board Ltd, Aylesbury, Bucks

Board Type: Chip
Backing: Kraft
Coating: Full
Hardsized: Yes

Coating Weight: 25 gsm
Recycled Content: 100%

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
415	300	Y	16.20	5.80
455	325	Y	20.30	7.20
490	350	Y	24.90	8.90
530	375	Y	29.90	10.90
570	400	Y	36.00	13.00
605	425	Y	43.00	15.50
645	450	Y	50.70	18.40
685	475	Y	57.00	21.30
720	500	Y	65.20	24.20
+/- 5%	+/- 3%		-15%	-15%

TEST DATA

Property	Test	Value	UOM	Tolerance
Brightness	ISO (R457)	79	%	Min 78%
Whiteness	ISO (D65/10)	84	%	
Cobb 180 Reverse	ISO 535	40	gsm	Max 50 gsm

TEST & TECH. NOTES

4 gsm reverse side sealer coating

MAKING NOTES

Min size: 450 x 550 mm LG

Max size: 2100 x 1600 mm SG

QUANTITY TOLERANCES

< 5 tonnes: +/- 15%

5-15 tonnes: +/- 10%

> 15 tonnes: +/- 5%

ORDERING INFORMATION