

Printa

Technical Specification

Description: F/C WLC grey back (GD2)
Mill: Mayr Melnhof Gernsbach

Board Type: Chip
Backing: Grey
Coating: Full

Coating Weight: 20 gsm

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
330	250	N	7.10	2.90
360	280	N	10.80	4.40
400	300	Y	12.80	5.60
430	320	Y	15.00	6.70
475	350	Y	19.20	8.60
500	380	Y	24.00	10.80
545	400	Y	28.10	12.50
570	420	N	32.00	14.00
575	425	N	32.50	14.40
610	450	Y	37.10	16.80
645	475	N	42.80	20.00
685	500	Y	50.00	23.20
760	550	Y	66.30	30.30
830	600	N	87.40	37.90
+/- 5%	+/- 2%		- 15%	- 15%

TEST DATA

Property	Test	Value	UOM	Tolerance
Smoothness	DIN 53107	100	ml/min	160 (max)
Brightness	ISO 11475	81	%	+/- 1
Gloss	ISO 8254	35	%	
Moisture content	EN 20287	6.5 - 7.5	%	+ / - 1%

TEST & TECH. NOTES

MAKING NOTES

Minimum sheet size 400 x 600 mm
Maximum sheet size 1600 x 1600 mm LG or SG
When either size >1400 mm, min pallet weight = 1t

QUANTITY TOLERANCES

ORDERING INFORMATION

< 1 t +/- 20%
1 - 2.5 t +/- 15%
2.5 - 5 t +/- 7.5%
> 5 t +/- 5%