

Tambrite

Technical Specification

Description: F/C FBB cream back (GC2)
Mill: Ingerois Board Mill

Board Type: Folding Box
Backing: Cream
Coating: Full

Coating Weight: 18 gsm

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
350	205	Y	10.20	4.80
400	225	Y	13.20	6.30
420	235	Y	15.30	7.20
440	245	Y	17.40	8.20
460	255	Y	19.90	9.20
480	265	Y	22.10	10.20
500	275	Y	24.70	11.30
540	290	Y	30.00	13.70
600	315	Y	37.50	17.30
650	340	Y	45.50	20.90
+/- 4%	+/- 4%		- 10%	- 10%

TEST DATA

Property	Test	Value	UOM	Tolerance
Smoothness	ISO8791-4	1	ums	max. 1,3
Brightness	ISO2470	86	%	+/- 2
Gloss	ISO8254-1	40	%	
Moisture content	ISO 287	8 - 9%		+ / - 1

TEST & TECH. NOTES

MAKING NOTES

Min sheet size 400 x 600 mm

Maximum sheet size ex-mill: 1300 x 1600 mm LG or 1600 x 1300 mm SG

Maximum sheet size ex-converter: 1565 x 2025 mm (Surcharge applicable)

Maximum reel size 2500mm. Cores: 127 mm, 153 mm, 254 mm, 305 mm.

QUANTITY TOLERANCES

ORDERING INFORMATION

1000 - 4999 Kgs +/- 10%

5000 - 14999 Kgs +/- 5%

15000 Kgs plus +/- 3%

Tambrite

Technical Specification

Description: F/C FBB cream back (GC2)
Mill: Ingerois Board Mill

Board Type: Folding Box
Backing: Cream
Coating: Full

Coating Weight: 18 gsm