

Zenith

Technical Specification

Description: F/C FBB white back (GC1)
Mill: Ningbo Zhonghua

Board Type: Folding Box
Backing: White
Coating: Full

Coating Weight: 20 gsm
Rev Coating Weight: 10 gsm

PRODUCT SPECIFICATION

Caliper	Gsm	Std	Mill Stiffness Taber 15° mNm	
			MD	CD
310	215	Y	8.80	4.00
355	235	Y	11.00	5.50
380	250	Y	14.30	7.50
415	270	Y	17.60	9.00
460	295	Y	24.80	12.10
510	325	Y	31.40	16.10
560	350	Y	38.50	18.70
610	380	Y	44.00	22.00
+/-4%	+/-3%		+0/-20%	+0/-20%

TEST DATA

Property	Test	Value	UOM	Tolerance
Smoothness (Top)	PPS	<=1.7	ums	
Brightness (Top)	ISO 2470	91	%	+/-2
Gloss	75	>=45	%	
Cobb (Top)	60s	<=55	gsm	
Moisture		6.0	%	+/- 1.5
CIE Whiteness		105 to 110		

TEST & TECH. NOTES

Sheet size tolerance: +/-2 mm

MAKING NOTES

Min sheet size: 450 x 640 mm LG

Max sheet size: 1100 x 1400 MG. If either side over 1200mm, packaging will be in stretch film rather than shrink wrap.

Min reel width: 300 mm. Max reel width: 1600 mm. Min 5t/spec. Min container dely

QUANTITY TOLERANCES

All quantities: +/- 10%

ORDERING INFORMATION